PATENT COOPERATION TREATY

PCT

REC'D	4 FEB 2005
WIPO	PCT

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

(Chapter II of the Patent Cooperation Treaty)

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference									
20021990 WO	FOR FURTHER ACT	TON See Form P	CT/IPEA/416						
International application No.	International filing date (day/month/year)	Priority date (day/month/year)						
PCT/FI 2003/000826	06.11.2003		07.11.2002						
International Patent Classification (IPC) o	r national classification an	d IPC							
C25C 7/02, C25C 1/16, C25B 9/02									
	• • •								
Applicant									
Outokumpu Oyj et al									
 This report is the international preliminary examination report, established by this International Preliminary Examining Authority under Article 35 and transmitted to the applicant according to Article 36. 									
2. This REPORT consists of a total of 4 sheets, including this cover sheet.									
3. This report is also accompanied by									
	and to the International B								
sheets of the description, claims and/or drawings which have been amended and are the basis of this report and/or sheets containing rectifications authorized by this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions).									
sheets which s	supersede earlier sheets, bu	t which this Authorit	ty considers contain an amendment that goes						
beyond the dis	sheets which supersede earlier sheets, but which this Authority considers contain an amendment that goes beyond the disclosure in the international application as filed, as indicated in item 4 of Box No. I and the Supplemental Box.								
b. (sent to the Internation	b. (sent to the International Bureau only) a total of (indicate type and number of electronic carrier(s))								
roadoblo form only on	, containing	g a sequence listing a	nd/or tables related thereto, in computer						
Administrative Instruc	tions).	ental Box Relating to	Sequence Listing (see Section 802 of the						
4. This report contains indications rel									
	the report	13.							
Box No. II Priority									
Box No. III Non-esta	ablishment of opinion with	th regard to novelty, inventive step and industrial applicability							
	Lack of unity of invention								
Box No. V Reasone									
	locuments cited	tions supporting such	i statement						
Box No. VII Certain o	defects in the international	application							
Box No. VIII Certain o	observations on the interna-	tional application							
Date of submission of the demand		Date of completion of	Estria						
	'	one of completion of	tuns report						
19.05.2004	1.	26 01 2005							
Name and mailing address of the IPEA/SE		26.01.2005							
Patent- och registreringsverket	['	Authorized officer							
Box 5055 S-102 42 STOCKHOLM		77 21	/						
Facsimile No. +46 8 667 72 88		Ulrika Nilsson/ELY Telephone No. +46 8 782 25 00							
Form PCT/IPEA/409 (cover sheet) (January	v 2004)	Cicphone No. +46	0 /02 25 UU						

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

International application No.

PCT/FI 2003/000826

Box No.	o. I Basis of the report	· · · · · · · · · · · · · · · · · · ·
1. With	ith regard to the language, this report is based on the international application in the language intervise indicated under this item.	n which it was filed, unle
	This report is based on a translation from the original language into the following language which is the language of a translation furnished for the purposes of:	,
	international search (under Rules 12.3 and 23.1(b))	
	publication of the international application (under Rule 12.4)	
	international preliminary examination (under Rules 55.2 and/or 55.3)	
	th regard to the elements of the international application, this report is based on (replacement this shed to the receiving Office in response to an invitation under Article 14 are referred to in this this contains the same of this report):	nt sheets which have bee report as "originally filed
	the international application as originally filed/furnished	
\boxtimes	the description:	
	pages <u>1-7</u>	originally filed/furnished
	pages* received by this Authority on	riginary mediumished
_	pages* received by this Authority on	
\bowtie	the claims:	1
	pagesas o	riginally filed/furnished
	pages* as amended (together with any str	itement) under Article 19
	received by this Authority on 22-10-	2004
	received by this Authority on	
	the drawings:	
	pages 1 as or	iginally filed/furnished
	received by this Authority on	
	received by this Authority on	
<u></u>	a sequence listing and/or any related table(s) - see Supplemental Box Relating to Sequence Listing	ng.
3.	The amendments have resulted in the cancellation of:	
	the description, pages	
	the claims, Nos.	-
	the drawings shoots/5	-
	the sequence listing (specify):	-
		<u> </u>
r 🗀	any table(s) related to the sequence listing (specify): This report has been established as if (some of) the amendments annexed to this report and limade, since they have been considered to go beyond the disclosure as filed, as indicated in the 70.2(c)).	sted below had not been Supplemental Box (Rule
	the description, pages	200 (2000)
•	the claims, Nos.	-
	the drawings, sheets/figs	_
	the drawings, sheets/figs the sequence listing (specify):	-
	the sequence listing (specify): any table(s) related to the sequence listing (specify):	- j
70.		
If item 4	4 applies, some or all of those sheets may be marked "superseded."]
rm PCT/IPE	PEA/409 (Box No. I) (January 2004)	

International application No.

PCT/FI 2003/000826

1.	Statement			
	Novelty (N)	Claims Claims	1-16	YES
	Inventive step (IS)	Claims Claims	1-16	YES NO
	Industrial applicability (IA)	Claims Claims	1-16	YES NO

2. Citations and explanations (Rule 70.7)

This statement is based on the claims 1-16 filed with the letter of October 22, 2004.

Documents cited in the International Search Report:

D1: US 4 015 099 A (WILLIAM SENIUK ET AL)

D2: US 2 790 656 A (L.A. COOK)

D3: US 4 035 280 A (RICHARD DEANE ET AL)

D4: EP 0 376 447 A1 (ZIMCO INDUSTRIES (PROPRIETARY) LIMITED

D5: DE 3 323 516 A1 (HAPAG-LLOYD WERFT GMBH)

D6: GB 2 252 569 A (BICC PUBLIC LIMITED COMPANY)

D1 discloses a process for fixing a Cu contact button to the Al or Al alloy conductor bar of an electrode plate. The process comprises (a) coating the Cu button with a thin layer of Ag; (b) mechanically screwing the Cu button in the conductor bar; (c) pre-heating the assembly; (d) welding the Ag-coated Cu button to the Al bar. The solid mechanical joint obtained by screwing is thus being reinforced by a strong metallurgical bond with a low electrical contact resistance.

D2-D6 represent less relevant prior art.

The documents do not disclose the special combination of features defined in the invention and D1 is therefore now reconsidered to only represent prior art. According to the

. . . / . . .

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

International application No.

PCT/FI 2003/000826

Supplemental Box

In case the space in any of the preceding boxes is not sufficient.

Continuation of: Box V

invention, a transmission layer is formed on the area on the lower surface of the support bar contact piece, the contact surface. After that the contact surface is coated with a silver or silver alloy having a thickness of 0.5-2 mm and the transmission layer and the coating form a metallurgical joint with the copper contact piece.

It is not considered obvious to a person skilled in the art to modify the known method or bar in D1 so as to obtain a method or support bar such as the ones claimed in the invention.

Therefore, the invention according to claims 1-16 is novel, considered to involve an inventive step and has industrial applicability.

Form PCT/IPEA/409 (Supplemental Box) (January 2004)

PATENT CLAIMS

A method for the formation of a good contact surface on a support bar of an aluminium cathode used in electrolysis, onto the end of which bar a copper contact piece is attached, wherein the cathode plate is immersed in an electrolysis cell and the support bar is supported by its ends on the sides of the electrolysis cell so that the contact piece is located on top of a busbar, characterised in that a transmission layer is formed on the area on the lower surface of the support bar contact piece, the contact surface, which is to touch the electrolysis cell busbar and after that the contact surface is coated with a silver or silver alloy having a thickness of 0,5 - 2 mm and the transmission layer and the coating form a metallurgical joint with the copper contact piece.

15

10

5

A method according to claim 1, characterised in that the transmission layer is tin or a tin-dominant layer.

20

- A method according to claim 1 or 2, characterised in that the silver or silver alloy layer is formed using soldering technique.
- A method according to claim 1 or 2, characterised in that the silver or silver alloy layer is formed using thermal spraying technique.

25

A method according to claim 4, characterised in that the thermal spraying technique is based on gas combustion.

A method according to claim 4 or 5, characterised in that the thermal spraying technique is high velocity oxy-fuel spraying.

30

A method according to claims 1 - 2 or 4 - 6, characterised in that silver or silver alloy is in powder form.

- 8. A method according to claim 4 or 5, **characterised in that** the thermal spraying technique is flame spraying.
- A method according to any of claims 1 2, 4 5 or 8, characterised in that silver or silver alloy is in wire form.

10

15

20

25

30

- 10. A method according to any of the above claims, characterised in that the contact surface is subjected to heat treatment after coating.
- 11. A method for the repair of contact surface of an aluminium cathode support bar used in electrolysis, wherein a copper contact piece is attached to one end of the support bar, in electrolysis the cathode plate is immersed into an electrolysis cell and the contact piece of the support bar is supported on the electrolysis cell busbar, characterised in that the lower surface acting as the contact surface of the support bar contact piece is first straightened out linearly and a transmission layer of tin is formed on the lower surface after that the contact surface is coated with silver or silver alloy having a thickness of 0,5 2 mm, so that the copper, tin and silver or silver alloy coating form a metallurgical joint.
- 12. A method for the repair of contact surface of an aluminium cathode support bar used in electrolysis, wherein a copper contact piece is attached to one end of the support bar and the lower edge of the contact piece is furnished with a notch, in electrolysis the cathode plate is immersed into an electrolysis cell and the support bar is supported on the electrolysis cell busbar at the notch, characterised in that the inclined sides of the notch act as the contact surface of the support bar contact piece, and are first straightened out linearly and then a transmission layer of tin is formed on the sides and after that the contact surface is coated with silver or silver alloy having a

thickness of 0.5 - 2 mm so that the copper, tin and silver or silver alloy coating form a metallurgical joint.

13. A support bar for an aluminium cathode used in electrolysis, where a cathode plate of the cathode is meant to be immersed in an electrolysis cell and the cathode support bar to be supported at its ends on the edge of the electrolysis cell, so that a contact piece of copper is attached to one end of the support bar, **characterised in that** the area of the lower surface of the support bar contact piece, the contact surface touching the busbar, has been coated with silver or silver alloy having a thickness of 0,5 – 2 mm and before coating, a transmission layer has been formed on the contact surface, the silver or silver alloy coating forming a metallurgical joint with the transmission layer and the copper of the contact piece.

14. A support bar according to claim 13, **characterised in that** the transmission layer is tin or a tin-dominant alloy.

- 15. A support bar according to claim 13 or 14, **characterised in that** the silver or silver alloy layer is formed using soldering technique.
- 16. A support bar according to claim 13 or 14, **characterised in that** the silver or silver alloy layer is formed using thermal spraying technique.

25

5

10

15

20